


마찰안정도시험

시험번호 : 아183

시험일자 : 2014-08-07

시험자 :

확인자 :



시료번호	두께1	두께2	두께3	두께4	두께평균	흐름값	안정도	보정계수	보정안정도		
	mm	mm	mm	mm	mm	mm	N		N		
1	63	63.2	63.1	62.9	63.05	4.23	4894	10.1125	4949		
2	63.3	63.1	63.3	63.5	63.3	4.086	4820	10.05	4844		
3	63.1	63.3	62.9	63	63.08	3.741	5182	10.105	5236		
4	62.9	63	63	63	62.98	5.382	5830	10.13	5906		
5	63.1	63.3	63.3	63	63.18	4.15	5820	10.08	5867		
6	62.9	63	63.1	63.1	63.03	4.492	5982	10.1175	6052		
Avr.	63.05	63.15	63.1167	63.0833	63.1033	4.34683	5421.33	10.0992	5475.67	#DIV/0!	#DIV/0!

Remarks :

